



## Glaze Colour


---




**GL-8004**  
Inclusion Orange  
Zr-Si-Cd-Se (1250°C)




**GL-8005**  
Inclusion Red  
Zr-Si-Cd-Se (1250°C)




**GL-8100**  
Peach  
Sn-Cr-Ca-Si (1300°C)




**GL-8111**  
Maroon  
Sn-Cr-Ca-Si (1300°C)




**GL-8201**  
Coral Pink  
Zr-Si-Fe (1250°C)




**GL-8202**  
Coral Pink  
Zr-Si-Fe (1250°C)




**GL-8301**  
Pr. Yellow  
Zr-Si-Pr (1250°C)




**GL-8303**  
Pr. Yellow  
Zr-Si-Pr (1250°C)




**GL-8501**  
Golden Brown  
Fe-Cr-Al-Zn (1300°C)



**GL-8512**  
Golden Yellow  
Fe-Cr-Al-Zn (1300°C)




**GL-8521**  
Red Brown  
Fe-Cr-Zn (1300°C)




**GL-8522**  
Red Brown  
Fe-Cr-Zn (1300°C)

# Glaze Colour


---




**GL-8531**  
Coffee  
Al-Cr-Fe-Mn(1250°C)




**GL-8601**  
Victoria  
Zr-Si-Pr-V (1250°C)




**GL-8611**  
Green  
Cr-Co-Al (1300°C)




**GL-8622**  
Peacock Green  
Co-Cr-Al-Zn (1300°C)




**GL-8701**  
Silver Grey  
Sb-Sn (1300°C)




**GL-8702**  
Grey  
Co-Fe (1300°C)




**GL-8801**  
Turquoise Blue  
Zr-Si-V (1300°C)




**GL-8811**  
Peacock Blue  
Co-Cr-Al-Zn (1300°C)




**GL-8821**  
Cobalt Blue  
Co-Al (1300°C)



**GL-8822**  
Cobalt Blue  
Co-Al (1300°C)




**GL-8871**  
Lilac  
Ca-Cr-Sn-Al (1300°C)



**GL-8901**  
Black  
Co-Cr-Ni-Fe-Mn (1250°C)


## Glaze Colour

---




**GL-8903**

Black  
Cr-Ni-Fe-Mn (1250°C)




**GL-7100**

Ivory  
Zr-Si-Pr-Fe (1250°C)




**GL-7202**

Co.Si.Blue  
Co-Si (1250°C)




**GL-7305**

Wooden  
Fe-Cr-Al-Zn (1300°C)




**GL-7404**

Sorento Blue  
Co-Al-Si (1300°C)




**GL-7507**

Purple  
Co-Al-Sn-Cr (1260°C)




**GL-7622**

Mint Green  
Cr-Zr-Si (1260°C)




**GL-7705**

P.Green  
Zr-Si-V (1250°C)




**GL-7813**

Osis Green  
Cr-Zr-Si (1280°C)



**GL-7817**

Vardhe Green  
Cr-Zr-Co-Al (1250°C)



**GL-7908**

Bhama Base  
Zr-Si-Fe (1250°C)

# Ceramic Glaze & Body Colour

## Product Technical Data Sheet

---

**Body Colour** is suitable for the surface Colour of internal Floor tiles / external Slab Tiles, Full Body Tiles, Double Charge Tiles & Glaze Colour is suitable for the surface Colour of internal wall tiles / external wall Tiles, Sanitary Ware and daily use ceramic. Mixing the different pigment can get multiple colours. And those colours can be used to make one of the best and remarkable ceramic products.

These are some of the technical details to keep in mind while selecting the product. Fire temperature range - 1200°C to 1300°C. The component of the basic **Body & Glaze Colour**, the firing atmosphere, the choice of emulsion, will affect the colour of pigment in Body & Glaze.

### General Information

Company : **FONIC COLOUR**

Product Type : **Ceramic Glaze & Body Colour**

Chemical Type : **In - Organic**

Testing Standard : **ASTM C 604 - 2002, GB/T 19077.1-2008, GB/T 16537 - 2010, GB/T1347-2008**

### Physical Properties

Appearance Dry; Odourless; Uncontaminated; Without coarse agglomerates

Density (g/cm<sup>3</sup>) : **0.9 to 1.20**

Average Particle Size (um)\* : **13.1**

D50 (um)\* : **13.71**

D97 (um)\* : **24.50**

M2/c.c. : **0.93; Soluble salt <0.25%; Ignition Loss (1025°C); 0.25mg/L; PH: 6.7-7.0 (10g/L)**

\*Testing instrument is OMEC Easysize 20 Laser Particle Size Analyzer

### Impurities

No metallic iron/ metals present in product from processing equipment or handling.  
pb<0.01 mg/L ; Cd<0.01 mg/L; Hg <0.1mg/L

### Transport

No dangerous substance (**EEC EINECS LISTING! 269-075-7**)

GS-CODE : **32071000**

Packaged in **25 kg** plain paper bag

### Application

Suitable firing temperatures : **1000°C~1300°C in oxide or slight reduce atmosphere**

**Note** : The analysis data in this document refers to the test report conducted by the third party

**Research Institute Testing Co Ltd.**