

Technical Data Sheet Tio2 Anatase Grade

Characteristics	Value
TiO2 Content (%)	≥ 98.5
Whiteness	≥ 90
SO3 Content (%)	≤ 0.15
Fe2O3 Content (%)	≤ 0.05
105 C Moisture	≤ 0.5
Fineness (45um Size Residue)	≤ 0.3
Ph Value	6.5-8

Technical Data Sheet TiO2 Rutile Grade

Characteristics	Value
TiO2 Content (%)	≥ 93.5
Rutile Content (%)	≥ 98.5
Whiteness (%)	≥ 98
Tint-reducing Powder(Reynolds number)	≥ 2000
Oil Absorption(g/100g)	≤ 18
105°C Volatile(%)	≤ 0.5
Fineness (45um Size Residue)	≤ 0.05
Matter soluble in water	≤ 0.5
Surface Treatment	ZR AL coating

FONIC COLOUR

Nr. A & J Microns Rajkot-Kandla Highway, Morbi By pass Road

Village :- Dharampur

Morbi-363642 (Gujarat) INDIA

Mo : + 91 8000 840 840

Info@foniccolour.com, raju@foniccolour.com

Web : www.foniccolour.com